

评价项目	条件	AS-3N	PURE-3
粒子计数	液体中	$35 \times 10^9/\text{m}^3$	$114 \times 10^9/\text{m}^3$
	气体中	$> 0.3 \mu\text{m}$ 88.4个/ $\text{ft}^3$	$> 0.3 \mu\text{m}$ 294.4个/ $\text{ft}^3$
蒸发残留物	DI	—	—
	IPA	$0.402 \mu\text{g}/\text{m}^3$	$0.115 \mu\text{g}/\text{cm}^3$
抽出离子	Na	71.50ppm( $\mu\text{g}/\text{g}$ )	76.90ppm( $\mu\text{g}/\text{g}$ )
	K	7.10ppm( $\mu\text{g}/\text{g}$ )	18.20ppm( $\mu\text{g}/\text{g}$ )
	Mg	4.57ppm( $\mu\text{g}/\text{g}$ )	1.97ppm( $\mu\text{g}/\text{g}$ )
	Ca	14.40ppm( $\mu\text{g}/\text{g}$ )	5.12ppm( $\mu\text{g}/\text{g}$ )
	Cl	33.30ppm( $\mu\text{g}/\text{g}$ )	29.50ppm( $\mu\text{g}/\text{g}$ )
重量	—	$25.00\text{g}/\text{m}^3$	$25.00\text{g}/\text{m}^3$
吸水性	—	$540\text{g}/\text{m}^3$	$504\text{g}/\text{m}^3$
抗拉强度	长	2.22kg	2.21kg
	宽	1.87kg	2.35kg
厚度	—	$400 \mu\text{m}$	$370 \mu\text{m}$